

**Product Data Sheet**  
Edition 27/06/2012  
Identification no:  
02 05 03 06 100 0 000005  
Sika® Polysulphide PG

# Sika® Polysulphide Pour Grade

Two component polysulphide sealant- Pourable Grade

## Product Description

Sika® Polysulphide PG is a cross linking polysulphide based elastic sealant for vertical and horizontal expansion joints.

## Uses

It is used in horizontal joints in many types of buildings and civil engineering constructions such as :

- Expansion joints in floors
- PQC joints, Precast concrete elements
- Bridge deck joints
- Vacuum dewatered floor joints/groove sealing, crack repairing
- Horizontal trafficable Joints, Airport runways, car park, roads and culverts
- Wherever a permanently flexible horizontal seal is required

## Characteristics / Advantages

- Easy to use
- Economical
- Good UV resistance & weatherability
- Excellent adhesion with many materials ,
- Good chemical resistance (alkalies & dilute acids, petrol, diesel or jet fuel and many solvent and vegetable oils)
- Permanently elastic

## Tests

**Approval / Standards** Confirms to : BS 5212 – 1990

## Product Data

### Form

**Appearance/Colour** Grey ,paste

**Packaging** 4 kg (Component A = 3.68 kg, Component B = 0.32 kg )

**Pot Life** ~145 minute at 30°C

### Storage

**Storage Conditions / Shelf-Life** 12 months from the date of production when stored properly in unopened undamaged and sealed original packaging in cool and dry condition at temperature +5°C to +30°C.

## Technical Data

**Chemical Base** Cross linking polysulphide

**Density** ~ 1.70 kg/l

Construction



## Mechanical / Physical Properties

<b>Joint Configuration</b>	Minimum Joint Width- 6 mm Maximum Joint Width - 50 mm* *(Under special conditions, up to 30mm. Please consult Sika® technical services )
<b>Width: Depth ratio</b>	For joints from 10 mm to 30 mm, width : Depth = 1 : 1* (For horizontal pedestrian areas (* Depending on the joint design)
<b>Curing Time</b>	24 hours
<b>Shore-A hardness</b>	< 10 (7 days)
<b>Movement capacity</b>	30% of average joint width
<b>Tack Free Time</b>	No adherence after a period of 16 ± 0.1 hrs
<b>Service temperature</b>	-5 <sup>0</sup> C to + 60 <sup>0</sup> C


## Application Details

<b>Substrate Quality</b>	All surfaces must be clean, dry and free from any loosely adhering particles
<b>Substrate Preparation</b>	Check the joints edges for soundness and if found weak cut recess and fill up with suitable repair mortar (Consult Sika Technical services). Correct joint depth can be established by inserting polyethylene based Sika® Backer Material tightly into the joint. When the joints have been filled with fibre filled board, this must be raked back to the required depth. Use bond breaker tape over the backer material. Protect surfaces with masking tape.
<b>Priming</b>	Sika® Primer-80 (Porous) should be used as a primer only on the two sides. Wait for 30 mins.

## Application Conditions / Limitations

<b>Substrate Temperature</b>	+10°C min. / +40°C max.
<b>Ambient Temperature</b>	+10°C min. / +40°C max.
<b>Material Temperature</b>	+10°C min. / +40°C max.
<b>Substrate Moisture Content</b>	Dry joint with sound concrete edges. For joints under wet conditions, use Sika® Primer-80 (Porous)

## Application Instructions

<b>Mixing</b>	Part A : Part B = 92 : 8 (by weight)
<b>Mixing Time</b>	 The two components are mixed in the ratio Comp. A : Comp B = 92 : 8 by weight with a low speed mixer (400 - 600 rpm). Mix for approximately 8 - 10 minutes until a smooth, even consistency is achieved.
<b>Application Method / Tools</b>	Where required, protect the surface with masking tape. Install the sealant into the joint without trapping air. Tool-off with a spatula to lightly concave profile. Remove masking tape.
<b>Cleaning of Tools</b>	Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.
<b>Notes on Application / Limitations</b>	Do not use in contact with drinking water or food. Gun grade Sika® Polysulphide PG is gun-applied - 2 part polysulphide sealant which is used both for horizontal and vertical joints. Pourable grade Sika® Polysulphide PG is used only in case of horizontal joints.

---

**Value Base**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

---

**Health and Safety Information**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

---

**Legal Notes**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---



Sika India Pvt. Ltd.  
Commercial Complex II  
620, Diamond Harbour Road  
Kolkata, 700 034, India

Phone +91 33 2447 2448/2449  
Telefax +91 33 2396 8688  
ind.sika.com  
info.india@in.sika.com